

**7NFRC** 

## Heritage Register Roofing Types

Slate/ tile type	Description	Geographic areas
CLAY TILES Not machine-made		
1.1 Peg Tiling	Hand-made clay plain tiles with large holes for use with wooden pegs (also used with mortar torching)	South and east of the M4 Corridor from The Wash to the Bristol Channel (south east of the Limestone Belt)
1.2 York Peg Tiling	Large format hand-made clay plain tiles with large holes for use with wooden pegs (also used with mortar torching)	Yorkshire region, centred around York
1.3 Plain Nib Tiling	Hand-made clay plain tiles with single or multiple nibs but with no holes for nailing, usually fixed with torching or selective spot bedding	Midlands and some Eastern Counties
1.4 Pan Tiling	Hand-made single-lap Roman and pantiles with notches or mitres laid to a fixed gauge, with or without torching	Eastern counties from Moray Firth to Kent, Bridgewater area and some isolated estates
SMALL RANDOM SLATE		
	small number of size-lengths and a large number of courses	
2.1 Limestone Slates (Alsoknown as stone tiles)	Head-fixed (nails or pegs) laid dry or with spot bedding	Area from Dorset to Lincolnshire along the Limestone belt, including the Cotswolds and around Brandsby in East Yorkshire
2.2 Limestone Slates (Also known as collyweston slates)	Head-fixed (nails or pegs) laid in mortar as an alternative to dry laying	Stamford, Lincolnshire and Northamptonshire region.
2.3 Slates (Alsoknownasblue slates) See 7.7	Various small metamorphic slates usually head-fixed and formerly torched, laid dry or spot bedded or head- bedded, fixed to laths, battens or boards, some known as Doubles or Peggies	All slate areas including West Country, Wales, Swithland, Westmorland, Cumbria, Galloway, Borders, Bute-Luss-Aberfoyle-Dunkeld, Foudland, Lorn – Easdale, Ballachulish and Northern Ireland
2.4 Slates (Triple-lap) See 7.7	Various small metamorphic slates usually head-fixed, laid dry, fixed to laths or battens, sometimes referred to as Scantle	West Country
2.5 Slates (Wet-laid) See 7.7	Various small metamorphic slates usually head-fixed to a triple-lap, laid with intermittent or continuous mortar tail bedding, fixed to laths or battens, sometimes referred to as Scantle	West Country
LARGE RANDOM SLATE Where setting out involves a	S large number of size-lengths and a small number of courses	often with only one course per size-length
3.1 Gritstone Slates (Alsoknownasgrey slates)	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding	Pennine counties north from Staffs, Derbyshire and Cheshire to the Scottish Border.
3.2 Red Sandstone Slates	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding	Cumbria, Eden Valley and Dumfries
3.3 Sandstone Slates	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding	Wealden area centred on Horsham
3.4 Sandstone Slates	Head-fixed to laths or battens to a single-lap with thin soaker slates to each perpend (under-and-over) and laid with mortar bedding	Wealden area centred on Horsham
3.5 Limestone Slates	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding	Area based on distribution from Portland, Purbeck, Sherborne and Bruton
3.6 Welsh Ton Slates (Also known as blue slates)	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding	Large thick randoms known as Bangor Ton Slates and distributed coastwise mainly around the Irish Sea and through the canal and river systems including Cheshire, Lancashire and Yorkshire
3.7 Welsh Queens Slates	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding	Fine large slates with same distribution as Bangor slates including by railway and coasta shipping around the UK

NATIONAL HERITAGE ROOFING CONTRACTORS REGISTER

**7NFRC** 

## Heritage Register Roofing Types

3.9 Burlington Slates	bedding	
(Also known as roundheads)	Head fixed or Centre-nailed randoms fixed to battens and laid dry with torching or spot bedding or to boards	coastal shipping around the UK Fine large slates distributed mainly by the canal and river system but including railway and coastal boats around the UK mainly northern
3.10 Rag Slates	Wide slates fixed direct to rafters at close-centres with nails and torched	Fine large slates from some West Country quarries mainly Cornish
MEDIUM RANDOM S		
	large number of size-lengths and a large number of courses,	with an increasing number of courses in each size-
4.1 Sandstone Slates	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding.	Bristol Channel and South Wales coal fields areas. Hereford, Shropshire, Fife, Angus, Moray, Caithness, Orkney and Shetland
4.2 Tilestones (Sandstone slates)	Head-fixed to laths or battens with pegs or nails and laid dry with torching or spot bedding	West and Mid Wales from Carmarthen to Shropshire
4.3 Schist Slates	Head-fixed to boards or battens with pegs or nails and laid dry with torching or spot bedding	Speyside
4.4 Slates See 7.7	Various metamorphic slates usually head-fixed and formerly torched, laid dry or spot bedded or head- bedded, fixed to laths or battens	West Country, Wales and Lake District
MODERN RANDOM SLA		
-	nange- course nail hole positions, size-lengths and number of	
5.1 Slates See 7.7	Various metamorphic slates centre-nailed to sawn battens, formerly torched but mainly laid over underlay, also boards mainly Scotland or complex work	West Country, Wales and Lake District distributed nationally
OTHER TYPES Usually confined to a small ar	rea and a special local material	
6.1 Diamond Pattern	Special stone slates of one size laid to battens and	Thornhill, Dumfries, and Angus regions.
(Also known as diagonal lapping)	similar to Roman slating	
6.2 Stone Slabs	Large flagstones laid under-and-over	Local to Caithness, Orkney and some small Pennine and Purbeck roofs.
6.3 Vaulting	Stone slabs laid under and over in conjunction with solid masonry	Central Scotland. Mainly religious buildings of castles
6.4 Patent Slating	Large metamorphic slates laid under-and-over to patent cast-iron or timber framing	On special buildings during Victorian period distributed by rail
6.5 Fire-proof Slating	Tally slates fixed to metal battens	
than torching and cleft hardw 7.2 Fixings - Many specificatio 7.3 Labour Skills - The differen setting out gauges for laying, t 7.4 Tally Slates - Whilst many	that the majority of roof conservation projects use an underla ood laths. ns substitute special nails for wooden pegs and are nailed into nees between the three groups of random slating is intended t together with local variations which are significantly different heritage roofs were originally covered or have been re-roofed stem, most trade classification A members of NFRC are compe	b battens rather than hooked over laths o differentiate between the skills of sorting and in each of the three categories. with regular sized (tally) slates, and this could be
fall into the same skill group a 7.6 Imitation - Imitation and a	e-lap tiles made by pressing, extrusion or machine manufactur s tally slates. rtificial modern slate and tile products are not included rds slates or slate is restricted to metamorphic slate rock. Slate	

7.7 Slates - The use of the words slates or slate is restricted to metamorphic slate rock. Slates from other rocks are qualified e.g. Limestone Slates.

7.8 Arts & Crafts - Some of the heritage roofing systems given above have been copied by designers of revival property in late 19<sup>th</sup> and early 20<sup>th</sup> centuries (notably limestone and tiles).